



ENNEATECH
ENGINEERING POLYMERS

Schmiedestraße 34
26629 Großefehn
Germany

+49 (0) 4943 91 99 0
info@enneatech.com
www.enneatech.com

ENTRON eco

reliable, ecological,
powerful

ENTRON eco

Top-class polyamide
compounds



up to 90% CO₂ reduction

providing the same quality
as new goods

ENTRON eco are our recycled polyamide compounds for demanding applications. Our sustainable performance for high-quality industrial manufacturing is guaranteed and certified. Your benefit: a reduction in your CO₂ footprint and new design scope thanks to the best material quality.

ENTRON eco A GF25 NC

NOTICE

The following information has been compiled to the best of our knowledge and represents the current status of our experience and knowledge. These specifications are product descriptions, however, in no case do they constitute guarantees of quality or durability. The user is obliged to carry out their own examinations and tests in their specific area of business when processing and using our products. The information cannot be transferred to other products made with our material.



COMPANY

ENNEATECH AG

Schmiedestraße 34 | 26629 Großefehn | Germany
+49 (0) 4943 91 99 0 | info@enneatech.com
www.enneatech.com



PRODUCT

Trade name **ENTRON^{eco} A GF25 NC**

Article number **70350**

Polymer **PA 6.6**

Colour **Natural coloured**

Melting temperature **255 - 265 °C (DSC)**

Filler content **25% Glass fibre**

Shape of the granules **Cylindrical**

PROPERTIES

Charpy impact strength [DIN EN ISO 179-1/1eU] **60** [kJ/m²]

Charpy notched impact strength [DIN EN ISO 179-1/1eA] **8** [kJ/m²]

Tensile modulus [DIN EN ISO 527-2 /1A] **7700** [MPa]

Tensile strength [DIN EN ISO 527-2 /1A] **160** [MPa]

Elongation at break [DIN EN ISO 527-2 /1A] **4** [%]

NOTICE

The following information has been compiled to the best of our knowledge and represents the current status of our experience and knowledge. These specifications are product descriptions, however, in no case do they constitute guarantees of quality or durability. The user is obliged to carry out their own examinations and tests in their specific area of business when processing and using our products. The information cannot be transferred to other products made with our material.

PROCESSING

Predrying	> 4h	80	[°C]
Melt temperature	< 10 min	270 - 300	[°C]
Mold temperature		70 - 90	[°C]

INFORMATION

Quality management	<u>ISO 9001 Certificate</u>	
Energy management	<u>ISO 50001 Certificate</u>	
Application	Injection moulding & extrusion	
Packaging	silos, bigbags, octabin, 25 kg bags	
Certificate of analysis	Available for each delivery (APZ 3.1 acc. DIN EN 10204)	
Product data sheet	<u>ENTRONeco A</u>	Technical data & specifications
Material safety information	<u>ENTRONeco A</u>	Product safety
Yearly compliance statement	<u>ENTRONeco A & B</u>	Regulations & yearly tests

NOTICE

The following information has been compiled to the best of our knowledge and represents the current status of our experience and knowledge. These specifications are product descriptions, however, in no case do they constitute guarantees of quality or durability. The user is obliged to carry out their own examinations and tests in their specific area of business when processing and using our products. The information cannot be transferred to other products made with our material.