



**ENNEATECH**  
ENGINEERING POLYMERS

Schmiedestraße 34  
26629 Großefehn  
Germany

+49 (0) 4943 91 99 0  
info@enneatech.com  
www.enneatech.com

# ENTRON eco

reliable, ecological,  
powerful

## ENTRON eco

Top-class polyamide  
compounds



**up to 90% CO<sub>2</sub> reduction**

providing the same quality  
as new goods

ENTRON eco are our recycled polyamide compounds for demanding applications. Our sustainable performance for high-quality industrial manufacturing is guaranteed and certified. Your benefit: a reduction in your CO<sub>2</sub> footprint and new design scope thanks to the best material quality.

## ENTRON eco B GF30 NC

### NOTICE

The following information has been compiled to the best of our knowledge and represents the current status of our experience and knowledge. These specifications are product descriptions, however, in no case do they constitute guarantees of quality or durability. The user is obliged to carry out their own examinations and tests in their specific area of business when processing and using our products. The information cannot be transferred to other products made with our material.



## COMPANY

ENNEATECH AG

Schmiedestraße 34 | 26629 Großefehn | Germany  
+49 (0) 4943 91 99 0 | [info@enneatech.com](mailto:info@enneatech.com)  
[www.enneatech.com](http://www.enneatech.com)



## PRODUCT

Trade name **ENTRON eco B GF30 NC**

Article number **60360**

Polymer **PA 6**

Colour **Natural coloured**

Melting temperature **220 - 230 °C (DSC)**

Filler content **30% Glass fibre**

Shape of the granules **Cylindrical**

## PROPERTIES

Charpy impact strength [DIN EN ISO 179-1/1eU] **90** [kJ/m<sup>2</sup>]

Charpy notched impact strength [DIN EN ISO 179-1/1eA] **15** [kJ/m<sup>2</sup>]

Tensile modulus [DIN EN ISO 527-2 /1A] **9800** [MPa]

Tensile strength [DIN EN ISO 527-2 /1A] **185** [MPa]

Elongation at break [DIN EN ISO 527-2 /1A] **4** [%]

## NOTICE

The following information has been compiled to the best of our knowledge and represents the current status of our experience and knowledge. These specifications are product descriptions, however, in no case do they constitute guarantees of quality or durability. The user is obliged to carry out their own examinations and tests in their specific area of business when processing and using our products. The information cannot be transferred to other products made with our material.

## PROCESSING

Predrying	> 4h	80	[°C]
Melt temperature	< 10 min	240 - 270	[°C]
Mold temperature		60 - 90	[°C]

## INFORMATION

Quality management	<u>ISO 9001 Certificate</u>	
Energy management	<u>ISO 50001 Certificate</u>	
Application	<b>Injection moulding &amp; extrusion</b>	
Packaging	<b>silos, bigbag, octabin, 25 kg bags</b>	
Certificate of analysis	<b>Available for each delivery (APZ 3.1 acc. DIN EN 10204)</b>	
Product data sheet	<u>ENTRON eco B</u>	Technical data & specifications
Material safety information	<u>ENTRON eco B</u>	Product safety
Yearly compliance statement	<u>ENTRON eco A &amp; B</u>	Regulations & yearly tests

### NOTICE

The following information has been compiled to the best of our knowledge and represents the current status of our experience and knowledge. These specifications are product descriptions, however, in no case do they constitute guarantees of quality or durability. The user is obliged to carry out their own examinations and tests in their specific area of business when processing and using our products. The information cannot be transferred to other products made with our material.