Schmiedestraße 34 26629 Großefehn Germany +49 (0) 4943 91 99 0 info@enneatech.com www.enneatech.com

# **ENTRON eco**

reliable, ecological, powerful



ENTRON eco are our recycled polyamide compounds for demanding applications. Our sustainable performance for high-quality industrial manufacturing is guaranteed and certified. Your benefit: a reduction in your CO<sub>2</sub> footprint and new design scope thanks to the best material quality.

# ENTRON eco B GF50 NC

## NOTICE

The following information has been compiled to the best of our knowledge and represents the current status of our experience and knowledge. These specifications are product descriptions, however, in no case do they constitute guarantees of quality or durability. The user is obliged to carry out their own examinations and tests in their specific area of business when processing and using our products. The information cannot be transferred to other products made with our material.



# ENTRONeco B GF50 NC



## COMPANY

**ENNEATECH AG** 

Schmiedestraße 34 | 26629 Großefehn | Germany +49 (0) 4943 91 99 0 | info@enneatech.com www.enneatech.com



PRODUCT	
Trade name	ENTRON eco B GF50 NC
Article number	60300
Polymer	PA 6
Colour	Natural coloured
Melting temperature	220 - 230 °C (DSC)
Filler content	50% Glass fibre
Shape of the granules	Cylindrical

PROPERTIES			
Charpy impact strength	[DIN EN ISO 179-1/1eU]	90	[kJ/m²]
Charpy notched impact strength	[DIN EN ISO 179-1/1eA]	17	[kJ/m²]
Tensile modulus	[DIN EN ISO 527-2 /1A]	15800	[MPa]
Tensile strength	[DIN EN ISO 527-2 /1A]	220	[MPa]
Elongation at break	[DIN EN ISO 527-2 /1A]	3.5	[%]

## NOTICE

The following information has been compiled to the best of our knowledge and represents the current status of our experience and knowledge. These specifications are product descriptions, however, in no case do they constitute guarantees of quality or durability. The user is obliged to carry out their own examinations and tests in their specific area of business when processing and using our products. The information cannot be transferred to other products made with our material.

# ENTRONeco B GF50 NC



PROCESSING				
Predrying	> 4h	80	[°C]	
Melt temperature	< 10 min	240 - 270	[°C]	
Mold temperature		60 - 90	[°C]	

INFORMATION			
Quality management	ISO 9001 Certificate		
Energy management	ISO 50001 Certificate		
Application	Injection moulding & extrusion		
Packaging	silo, bigbag, octabin, 25 kg bags		
Certificate of analysis	Available for each delivery (APZ 3.1 acc. DIN EN 10204)		
Product data sheet	ENTRON eco B	Technical data & specifications	
Material safety information	ENTRON eco B	Product safety	
Yearly compliance statement	ENTRON eco A & B	Regulations & yearly tests	

## NOTICE

The following information has been compiled to the best of our knowledge and represents the current status of our experience and knowledge. These specifications are product descriptions, however, in no case do they constitute guarantees of quality or durability. The user is obliged to carry out their own examinations and tests in their specific area of business when processing and using our products. The information cannot be transferred to other products made with our material.